Sintering of Composite Ceramic based on Corundum with Additive in the Al₂O₃-TiO₂-MnO System

Aung Kyaw Moe, Lukin Evgeny Stepanovich, Popova Nelya Alexandrovna

Abstract—In this paper, the effect of the additive content in the Al_2O_3 -TiO_2-MnO system on the sintering of composite ceramics based on corundum was studied. The samples were pressed by uniaxial semi-dry pressing under 100 MPa and sintered at 1500 °C and 1550 °C. The properties of composite ceramics for porosity and flexural strength were studied. When the amount of additives increases, the properties of composite ceramic samples are better than samples without additives.

Keywords-Ceramic, composite material, sintering, corundum.

I. INTRODUCTION

CERAMIC materials are widely used in various industries, often under extreme conditions under the influence of thermal, mechanical and other types of loads. At present, technical ceramics is an independent class of materials and its increasingly used in various branches of technology and industry such as electrical engineering, power engineering, including nuclear, radio engineering, metallurgy, chemical engineering. It is practically impossible to produce highquality products from such powders without the use of special additives. Therefore, one of the main problems in the technology of modern oxide ceramics is the development of methods for obtaining powders of specified dispersion, particle shape and activity for sintering [1]-[3].

From the theory and practice of solid-phase synthesis, it is known that sintering of powdery materials can be achieved by adding additives of foreign substances due to the formation of solid solutions and free vacancies in the lattice. From publications some additives strongly can accelerate the sintering of α-Al₂O₃. For example, TiO₂ and MnO can reduce the sintering temperature and MgO can regulate the crystallization of corundum or improve the individual properties of ceramics [4]. The addition of TiO₂ causes an intensive growth of grain of corundum ceramics up to 200-350 $\mu m.$ The solubility of TiO_2 in $\alpha\text{-}Al_2O_3$ is too low. This is determined by the shift in the lattice parameters of α-Al₂O₃. A solid solution of TiO₂ in α-Al₂O₃ is formed at a temperature of 1150 °C, and the solubility is 0.27% at 1300-1700 °C. Outside the solubility limit, excess TiO_2 coexisted with α -Al₂O₃ as rutile below 1350 °C and as Al₂TiO₅ above 1450 °C [5]. The role of MnO is very effective for controlling anomalous grain growth and achieving a density in the sintering of α -Al₂O₃. This leads to a decrease in the tendency to rupture of the poreborder and to adequate protection against abnormal grain growth. Combinations of manganese and titanium oxides were the most effective in lowering the sintering temperature, especially when present in equal amounts. The microstructure of such a ceramic usually consists of uniform dimensions and equiaxed grains of aluminum oxide [6], [7].

State diagram of Al_2O_3 -TiO₂-MnO system is a noncondensed one, in which the phase stability is determined not only by the temperature and composition but also by the oxygen partial pressure in the gaseous phase. In air, it was observed that the evolution of oxygen as the temperature rises is not easily reversed on cooling. In the other words, the hightemperature reduced forms tend to be retained at lower temperatures. This will be more the case when other components are present, with which the reduced oxide can react. Therefore, the phase equilibrium relationships in the system Al_2O_3 -TiO₂-MnO₂-MnO can be approximated by those for the Al_2O_3 -TiO₂-MnO system at temperatures above 800 °C [8].

Corundum ceramic based composite additives have been extensively studied because of their excellent properties such as high hardness, low electrical conductivity, good chemical stability, and oxidation resistance [9].

The purpose of this research is to obtain composite ceramics based on corundum α -Al₂O₃ with eutectic additives in the Al₂O₃-TiO₂-MnO system and to study its properties depending on the additive mass content and the temperature effect. To use as eutectic additives, a particularly suitable composite material with high strength and average pore size. Average pore size, porosity, density and mechanical strength of the ceramic materials are depending on concentration of the additive, pressing pressure and firing temperature.

When firing ceramic billets, various physical and chemical processes can occur: thermal decomposition of raw materials, chemical reactions between components or with the gaseous medium, polymorphic transformations, eutectic melting, dissolution of solid phases in the melt, crystallization from the melt of others. These processes can be accompanied by a change in mass, volume, chemical and phase composition, density and porosity.

II. EXPERIMENTAL

Corundum was obtained from alumina by melting in electric arc furnace and containing more than 98% α -Al₂O₃. Corundum is used as a structural ceramic due to having good

Aung Kyaw Moe is PhD student with The Department of chemical technology of ceramics and refractories, Dmitry Mendeleev University of Chemical Technology of Russia. Russian Federation. (phone: +7 (926) 725-49-07; e-mail: autumnghost4@gmail.com).

Lukin Evgeny Stepanovich is a Professor and Popova Nelya Alexandrovna is senior teacher with The Department of chemical technology of ceramics and refractories, Dmitry Mendeleev University of Chemical Technology of Russia, Russian Federation.

International Journal of Chemical, Materials and Biomolecular Sciences ISSN: 2415-6620 Vol:12, No:7, 2018

mechanical properties and also excellent thermal properties at high temperatures. As base material powder was used corundum F600. The average particle size of corundum powder (F600) is $D_{50} = 10$ MKM. Figs. 1 and 2 represent the microstructure and crystal structure of corundum powder F600 [9].



Fig. 1 Microstructure of corundum powder F600



Fig. 2 Crystal structure of corundum powder F600

In the state diagram of Al_2O_3 -TiO₂-MnO system, the concentrations of the eutectic materials were used as the following compositions (A) 30% Al_2O_3 , 17% TiO₂, 53% MnO at eutectic temperature 1580 °C. Fig. 3 represents the state diagram of Al_2O_3 -TiO₂-MnO system [10].



Fig. 3 The state diagram of Al₂O₃-TiO₂-MnO system

The raw materials powder components of eutectic additive were Al(OH)₃, MnCO₃, TiO₂. To obtain eutectic additive, the

raw materials powder components were heated to high temperature at 1000 °C, in order to achieve constant mass, occurring reactions at high temperature, burning impurities and organic substances.

After heating, components of eutectic additive with constant mass were mixed in Teflon ball mill grinding pot, the ratio of grinding balls and material was 1: 1. The total mixing time was 24 hours. And then, synthesis was carried out combining eutectic additive powder at high temperature 1200 °C. After synthesis, eutectic additive was comminuted 30 minutes in planetary mill, the ratio of grinding balls: material: ethanol (polyvinyl alcohol) was 3: 1: 2.5. Liquid compound was drying for 48 hours at the temperature of 80 °C, and eutectic additive was obtained.



Fig. 4 (a) Dry mixing eutectic additive in Teflon ball mill, (b) Wet mixing eutectic additive in planetary mill

The content of additives 1, 3, 5, and 7% were mixed with corundum in Teflon ball mill grinding pot by using dry milling method, the ratio of grinding balls and material was 1: 1. The total milling time of the charge was 1 hour. Composite ceramic powders with the ratio of corundum and additive 93/7, 95/5, 97/3 and 99/1 were formed a cylindrical disk shape (diameter=20 mm, high=4.9 mm and the mass of the sample was 4 g) in the uniaxial semi-dry pressing machine. The forming pressure was 100 MPa.



To obtain samples of composite ceramics with improved density and sufficient strength, samples were sintered at 1500 and 1550 °C in the furnace with lanthanum chromite heating rods. The samples were heated from room temperature to 1500

and 1550 °C. The temperature rate was 200 °C/hour, the holding time at 1500-1550 °C was 2 hours, temperature is reduced from 1500-1550 °C to 800 °C by the rate of 100 °C/hour.



Fig. 6 Technological process of composite ceramic sintering

Open porosity of the composite ceramic samples was calculated by the following equations:

$$\Pi_0 = \phi * W \tag{1}$$

$$\varphi = \frac{(M_{dry}*\rho_{water})}{(M_{wet}-M_{in water})}$$
(2)

$$W = \frac{M_{wet} - M_{dry}}{M_{dry}} * 100$$
(3)

where Π_0 is the open porosity (%), ϕ is the true density of ceramic samples (g/cm³), M_{dry} is the dry mass of sample (g), ρ_{water} is the density of the water (1g/cm³), M_{wet} is the wet mass of sample (g), M_{in water} is the mass in water (g), and W is the water absorption (%).

Flexural strength is the measure of the maximum stress per unit area that the specimen can withstand without breaking when it is bent. In the other words, it is defined as the ability of a material to withstand deformation under load. In Fig. 7, the three-point diagram of the flexural strength test is presented.



Fig. 7 Three-point diagram of the flexural strength test

To measure the flexural strength, a three-point bend was used in accordance with ASTM C1161-90 [11]. The flexural strength was calculated using the formula:

$$\sigma_{flexural} = \frac{3PL}{2bh^2} \tag{4}$$

where $\sigma_{flexural}$ is the flexural strength (MPa), P is the fracture load, L is the length between two span, b is the width, h is the high of sample.

III. RESULTS AND DISCUSSION

Samples containing 1, 3, 5 and 7 % by weight of the additive are already sintered at 1500 °C to a residual porosity of less than 0.5 %, at which the composition has a sufficiently high strength. With the increase in the content of the additive, the open porosity of the samples decreases from 7.14 to 0.16 % at a temperature of 1500 °C. The results on the sintering of samples with the addition of composition (A) in the Al₂O₃-TiO₂-MnO system are given in Table I.

TABLE I PROPERTIES OF COMPOSITE CERAMIC SAMPLES AT TEMPERATURE 1500°C Ratio of Open porosity Average density Flexural strength corundum and (%) (g/cm^3) (MPa) additive (%) 26.42 Pure corundum 3.03 75±10 99/1 7.14 3.58 157 + 1097/3 0.45 3.87 219±10 95/5 0.33 3.92 225±10 93/7 248±10 0.16 3.94

At a temperature of 1500 °C, the flexural strength of pure corundum is 75 MPa. But, the flexural strength increases 248 MPa with an additive content of 7%.





Fig. 8 Properties of composite ceramic samples at temperature 1500 °C: (a) – Average open porosity of composite ceramic samples (%), (b) – Flexural strength of composite ceramic samples (MPa)

At a temperature of 1550 °C with the increase in the content of the additive, the open porosity of the samples decreases from 1.49 to 0.29%. The results on the sintering of samples with the addition of composition (A) in the Al_2O_3 -TiO₂-MnO system are given in Table II.

TABLE II			
PROPERTIES OF COMPOSITE CERAMIC SAMPLES AT TEMPERATURE 1550 °C			
Ratio of corundum	Open	Average	Flexural strength
and additive (%)	porosity (%)	density (g/cm ³)	(MPa)
Pure corundum	21.53	2.95	87±10
99/1	1.49	3.74	207±10
97/3	0.63	3.82	210±10
95/5	0.33	3.85	218±10
93/7	0.29	3.87	223±10
25 20 (%) Atisound used 10 5 0 0 0%	21,53	0,63 0,33 3% 5%	(a)
R	atio of corundu	m and additive (%)
²⁵⁰			
(a) (a) (b) (b) (c) (c) (c) (c) (c) (c) (c) (c) (c) (c	20'	7 210 21	8 223
о _{ци} 150 -			
100 -	87		(b)
- 50 -			
<u> </u>	- I - I	1 1	i
0% 1% 3% 5% 7%			
Ratio of corundum and additive (%)			

Fig. 9 Properties of composite ceramic samples at temperature 1550
°C: (a) – Average open porosity of composite ceramic samples (%),
(b) – Flexural strength of composite ceramic samples (MPa)

IV. CONCLUSION

When sintering occurred, the shape of the grain changes by densification and mass transport occurs by volume and grain boundary diffusion. But, eutectic additive powder must be occurred the formation of a viscous liquid (liquid + solid) that filled the pore spaces and combined with corundum powder. So, the use of a dispersed powder as an additive to the eutectic composition in the Al_2O_3 -TiO₂-MnO system makes it possible to produce a dense material with a residual porosity of less than 0.1%, a flexural strength of more than 250 MPa using corundum.

ACKNOWLEDGMENT

This work was supported at The Department of chemical technology of ceramics and refractories, Dmitry Mendeleev University of Chemical Technology of Russia. Russian Federation.

REFERENCES

- A. R. Murzakova, U. Sh. Shayakhmetov, I. M. Valeev, "Technology of effective multifunctional ceramic composite materials (Refractories and Technical Ceramics)," 2012, №1-2, pp. 37–39.
- [2] S. V. Matrenin, A. I. Slossman, "M 34 Technical Ceramics (Textbook. -Tomsk: TPU Publishing House)," 2004, pp.75.
- [3] E. S. Lukin, N. Andrianov, N. B. Mamaeva, "On the problems of obtaining oxide ceramics with regular temperature (Refractories)," 1997, № 5, pp. 11–15.
- [4] P. Vudnikov, A.V. M. Ginstling, "Reactions in mixtures of solids," Gosstroyizdat, 1961.
- [5] G. Tiloca, "Thermal stabilization of aluminium-titanate and properties of aluminium-titanate solid solutions"; 1 Journal of material science 26 2809-2814(1991).
- [6] II.-S. Bae, S. Baik, "Abnormal growth of alumina," J. Am. Ceram. Soc. 80 (1997) 1149–1156.
- [7] Takashi Shirai, Hideo Watanabe, Masayoshi Fuji, Minoru Takahashi, "Structural Properties and Surface Characteristics on Aluminum Oxide Powders Ceramics".
- [8] Oliveira, V. A. G. & Brett, N. H, "Phase equilibria in the system MgO-Mn2O-MnO-CaSiO3 in air." J. de Phys., 47(2) (1986) C1-453-459.
- [9] Abhishek Kumar, MXC 230, Tel: 36888, "TP3 Ceramics: Sintering and Microstructure".
- [10] V. P. Borzakovskiy, A. I. Boykova, N. N. Kurtseva, V. V. Lapin, N. A. Toropov, "State Diagrams of silicate systems (tri silicate systems)," 1972.
- [11] N. T. Andrianov, A. V. Belyakov, A. S. Vlasov, I. Ya. Guzman, E. S. Lukin, M. A. Malkov, Yu. M. Mosin, B. S. Skidan, "Workshop on ceramics technology," 2004.