Study on the Electrochemical Performance of Graphene Effect on Cadmium Oxide in Lithium Battery

Atef Y. Shenouda, Anton A. Momchilov

Abstract—Graphene and CdO with different stoichiometric ratios of Cd(CH₃COO)₂ and graphene samples were prepared by hydrothermal reaction. The crystalline phases of pure CdO and 3CdO:1graphene were identified by X-ray diffraction (XRD). The particle morphology was studied with SEM. Furthermore, impedance measurements were applied. Galvanostatic measurements for the cells were carried out using potential limits between 0.01 and 3 V vs. Li/Li⁺. The current cycling intensity was 10⁻⁴ A. The specific discharge capacity of 3CdO-1G cell was about 450 Ah.Kg⁻¹ up to more than 100 cycles.

Keywords-CdO, graphene, negative electrode, lithium battery.

I. INTRODUCTION

THE ever growing demand of the portable electronics industry, the electric vehicle market, and storage for alternative energy sources has put energy storage devices at the forefront of technological investigations [1], [2]. While there may be many ways to store the intermittent power that is from alternative energy resources, the demands and direction of progress of the portable electronic and electric vehicle industries relies heavily on electrochemical storage devices, both batteries and supercapacitors. This dependence on electrochemical storage devices has specifically focused research attention on lithium ion batteries.

The electrochemical storage of energy and its conversion is of great interest for many practical applications. Electrical energy can be stored through primary and secondary (rechargeable) batteries. The rechargeable lithium ion batteries for portable electronic devices (e.g. PC and laptop computers, wireless and mobile phones, camcorders, etc.) have lately a strong tendency to expansion [3]-[13].

The effect of graphene on tin oxide prepared was studied through hydrothermal preparation [14]. The reversible specific capacity of Li/SnO–graphene (3:1) cell was about 930 Ah.Kg⁻¹ after 100 cycles. These results indicate that 3 SnO/1 graphene possesses superior cycle performance and high rate capability. The enhanced electrochemical performances with graphene can be attributed to the regulation in the volume change of the metallic tin through the prevention for the detachment and agglomeration of pulverized tin.

Fine CdO nanoparticles and CdO/Carboxylated multi walled carbon nanotube (CNT) nanocomposites were synthesized via a facile solution method for the first time and characterized by XRD, transmission electron microscopy and electrochemical measurements [15]. As a novel anode material for lithium-ion batteries, the nanosized CdO can deliver an initial capacity as high as 805 Ah.Kg⁻¹. However, the capacity retention of pure CdO is poor. By incorporating CNTs and water-soluble sodium alginate binder, the CdO could deliver a reversible capacity of 810 Ah.Kg⁻¹ up to 100 cycles and a capacity of 720 Ah.Kg⁻¹ even at the rate of 1500 AhKg⁻¹. To better understand the mechanism of the improvements, ex-situ SEM and Energy-dispersive X-ray spectroscopy (EDX) measurements are performed. Our findings would shed light on optimizing the electrochemical performances of other electrodes for lithium-ion batteries and the anodes of Ni-Cd batteries.

Well dispersed CdCO₃/carboxylated CNTs nanocomposites were synthesized via a facile/CNTs nanocomposites delivered an initial reversible capacity of 876 mAhg⁻¹ solution method [16]. As a novel anode material for lithium-ion batteries, the CdCO₃ had a better cycle ability. The superior electrochemical performance can be attributed to its unique hierarchy architecture, which facilitates the electron transport and accommodates the large volume change during the alloying/ de-alloying reactions.

It was reported that a compound such as CdO, which can react with Li via both of alloying–de-alloying and conversion reactions would be a good choice for investigation. CdO is an important semiconductor with a density of 8.15 Kg m⁻³ and relatively low cost. It has been used as the anode for Ni-Cd batteries due to its reversible Cd \leftrightarrow CdO conversion reaction. Moreover, the Cd can alloy with 3 mol lithium to form Li₃Cd, the total reaction CdO + 5Li \leftrightarrow Li₃Cd +Li₂O can deliver a high theoretical capacity of 1046 Ah.Kg⁻¹ with 5 mol lithium ion consummation [17].

The main challenge of anode materials is the huge volume change during the reversible conversion and alloying process which will lead to pulverization and loss of electrical contact within an electrode and thus to capacity fading [18]-[21]. Intense attempts have been made to address the volume change issues with incremental improvements by minimizing the particle size or incorporating inert buffers to alleviate the fracture and pulverization. Carbon and carbon derivatives such

A. Y. Shenouda is with the Central Metallurgical Research and Development Institute. (CMRDI) P.O. Box 87 Helwan, Egypt (corresponding author, phone: +201060628564; fax: +20227142451; e-mail: ayshenouda@ gmail.com).

A. A. Momchilov is in the Institute of Electrochemistry and Energy Systems (IEES), Sofia, Bulgaria (e-mail: aamomch@bas.bg).

as graphene beside CNTs are well-known due to its special 3D structure, superior electronic conductivity, large activated surface area and flexibility. Incorporation transition metal oxides with CNTs have been considered to be a promising method to improve their electrochemical performance. The CNTs serves not only as a conductive agent, but also as an inactive confining buffer to accommodate the volume change during electric cycling [22]-[24].

The aim of this work is to study the effect of graphene on CdO as anode material for lithium batteries as we found a few articles deal with the effect of carbon on CdO.

II. EXPERIMENTAL SECTION

A. CdO and Graphene Preparation and Characterization Steps

Graphene and CdO with ratios: 0:1, 1:1, 1:2, 1:3, 1:4 and 1:5 samples were prepared by hydrothermal reaction using stoichiometric ratios weights from Cd(CH₃COO)₂, ammonia solution and graphene. The solution mixture was stirred and heated firstly, at about 15 0°C using hot plate to form Cd(OH)₂. Finally, the active mixture was transferred into an autoclave and heated at 250 °C for 24 h. The crystalline phases of pure CdO and 3CdO:1graphene were characterized by XRD using Cu-K_a (λ = 1.5406 nm) radiation. The particles morphology was studied with a scanning electron microscope (JEOL, model JSM-5040).

B. Electrochemical Cell Assemble Process

The working electrode (WE) was prepared from slurry (200 mg) of the 70% active material, 15% C- black and 15% binder (polyvinyledine difluoride: PVDF). The slurry was pasted with some drops of N-methyl pyrrolidone (NMP) to form the active material. Copper disk substrate was coated with some of the active material to form the WE. The WE was dried in vacuum oven at 100 °C. A Teflon cell was used to house the lithium foil metal that acts as counter and reference electrode, separator of Celgrad (micro-porous poly propylene). The electrolyte was 1M LiClO₄ dissolved in propylene carbonate (PC).

C. Electrochemical Measurements

Galvanostatic charging and discharging cycling of the cells were achieved with potentials windows between 0.01 and 3V vs. Li/Li^+ using charging and discharging current intensity of 10^{-4} A. Furthermore, impedance measurements were applied using frequency range between 10^6 and 10^{-2} Hz using amplitude of 10 mV using Parastat 4000, Princeton, USA.

III. RESULTS AND DISCUSSION

The XRD pattern is shown in Fig. 1 for CdO nanoparticles, the diffraction peaks are absorbed at 2θ values. All the intense XRD patterns can be indexed to a pure face centered cubic phase structure CdO. The synthesis of graphene and its characterization was reported in a previous work [14].



Fig. 1 XRD spectra of CdO (a) and 3 CdO/graphene (b)

The main peak has been used to estimate the grain size of sample with the help of Scherrer equation [7]:

$$x = \frac{0.9\lambda}{\beta \cos\theta} \tag{1}$$

where λ is the wavelength ($\lambda = 1.5418 \text{ A}^{\circ}$) (Cu K_a), β is the full width at the half-maximum of the line and θ is the diffraction angle. The grain size estimated using the relative intensity peak (111) at 33.04° for CdO particles was found to be 60.3 nm. The (111), (200), (220), (311) and (222) reflections are clearly seen and closely match the reference patterns for CdO (Joint Committee for Powder Diffraction Studies JCPDS No. 78-0653) [15]. Also, the XRD pattern of CdO with graphene is similar to CdO one besides the peak of grapheme at 26°. The crystallite size of CdO with graphene particles was about 29.83 nm, which explains the effect of graphene in reducing the particle size. This is similar to CdO [15].

The morphology of the samples was investigated by SEM as shown in Fig. 2. The pure CdO is displayed as prismatic particles with the particle size of $1-2 \ \mu m$ (Fig. 2 (a)). However, it can be seen that the CdO/graphene (Fig. 2 (b)) is composed of fine CdO nanoparticles covered with graphene layers. The diameter of CdO nanoparticles is about 1 μm .

Electrochemical impedance spectroscopy (EIS) is considered an important technique for the study of the electrode and electrolyte/interface behavior due to surface interchanges [7]. The electrochemical impedance spectra of the cells, as presented in Fig. 3, show R_e at high frequency.

The charge transfer resistance, $R_{\rm ct}$, is equal to the semicircle. The plot of the real part of the impedance, $Z_{\rm re}$, versus the reciprocal root square of the lower angular frequencies is displayed in Fig. 4.

There are straight lines in the low frequencies that are attributed to the diffusion of the lithium ions into the bulk of the electrode material, or the so-called Warburg diffusion. This relation is governed by (2).

It is observed that the Warburg impedance coefficient, σ_w , is 515 Ω .s^{0.5} for the Li/3CdO-1G cell, and it has the lowest value in comparison with the other cells. The parameters of

the equivalent circuit are presented in Table I. Also, the diffusion coefficient values of the lithium ions for diffusion

into the bulk electrode materials have been calculated using (3) and are recorded in Table I.



Fig. 2 FESEM of CdO and 3CdO/graphene



ζ' [Ω] Fig. 3 EIS measurements of CdO and different ratios of CdO/graphene



Fig. 4 The plot of real impedance vs. reciprocal root square of angular frequency for the difference cells

$$Z_{\rm re} = R_{\rm e} + R_{\rm ct} + \sigma_{\rm w} . \omega^{-0.5}$$
⁽²⁾

$$D = 0.5 \left(\frac{RT}{A F 2 \sigma w C}\right)^2$$
(3)

$$Z_{re} = R_e + R_{ct} + 2\sigma_w^2. C_{dl}$$
 (4)

The double layer capacitance is given by:

$$\omega = \frac{1}{\text{Rct.Cdl}}$$
(5)

where R_{ct} : charge transfer resistance, R_e : electrolyte resistance, ω : angular frequency in low frequency region, D: diffusion coefficient, R: the gas constant, T: the absolute temperature, F: Faraday's constant, A: the area of electrode surface, and C: molar concentration of Li⁺ ions [13], [25].

| IABLE 1 EIS of LI/CDO-GRAPHENE CELLS | | | | | |
|--|------------------|---------------------------------|------------|------------------------|---------------------|
| Cell | $R_{ct}[\Omega]$ | $\sigma_w [\Omega \; s^{0.5}]$ | $D[m^2/s]$ | i° [Am ⁻²] | C _{dl} [F] |
| 1CdO-1G | 9792 | 32727 | 3.31E-19 | 2.62E-05 | 1.625E-09 |
| 2CdO-1G | 442 | 4632 | 1.65E-17 | 5.81E-04 | 3.60E-07 |
| 3CdO-1G | 363 | 515 | 1.33E-15 | 7.08E-04 | 4.38E-06 |
| 4CdO-1G | 598 | 11693 | 2.59E-17 | 4.30E-04 | 2.66E-07 |
| 5CdO-1G | 935 | 12502 | 2.26E-17 | 2.75E-04 | 2.69E-08 |
| CdO | 115432 | 38293 | 2.41E-19 | 2.23E-06 | 1.37E-10 |

The obtained diffusion coefficient $(1.33 \times 10^{-15} \text{ m}^2 \text{s}^{-1})$ for the Li/3CdO-1G cell explains the higher mobility for Li⁺ ion diffusion than in the other cell. Furthermore, the exchange current density is given by:

$$i^{\circ} = RT/nFR_{ct} \tag{6}$$

where n is the number of electron involved in the electrochemical reaction. Therefore, the charge-transfer reaction of 3CdO-1G electrode is stronger than in the other electrodes.

Fig. 5 shows the curves of the discharge capacity vs. the

cycle number of the samples. The specific discharge capacity of 3CdO-1G cell delivered about 450 Ah.Kg⁻¹ up to more than 100 cycles. Also, this cell has a higher specific discharge capacity rather than the other cells.



Fig. 5 The cycle life performance of Li / CdO-graphene cells

IV. CONCLUSION

All the intense XRD patterns can be indexed to a pure face centered cubic phase structure CdO. The grain size estimated using the relative intensity peak for CdO particles was found to be 60.3 nm. Also, the XRD pattern of CdO with graphene is similar to CdO one beside the peak of graphene at 26°. The crystallite size of CdO with graphene particles was about 29.83 nm, which explains the effect of graphene in reducing the particle size. The morphology of CdO is displayed as prismatic particles with the particle size of 1-2 µm. However, it can be seen that the CdO/graphene is composed of fine CdO nanoparticles covered with graphene layers. The diameter of CdO nanoparticles is about 1 µm. EIS measurements revealed that the Warburg impedance coefficient, σ_w , is 515 Ω .s^{0.5} for the Li/3CdO-1G cell, and it has the lowest value in comparison with the other cells. The obtained diffusion coefficient (1.33x10⁻¹⁵ m²s⁻¹) for the Li/3CdO-1G cell explains the higher mobility for Li⁺ ion diffusion than in the other cell. The specific discharge capacity of 3CdO-1G cell is about 450 Ah. Kg^{-1} up to more than 100 cycles.

ACKNOWLEDGMENT

The authors would like to thank Academy of Scientific Research and Technology (ASRT) for financial support of this work through the joint project of Egypt-Bulgaria cooperation.

REFERENCES

- M. Armand and J. M. Tarascon, "Building Better Batteries," *Nature, vol.* 451, pp. 652-657, Feb. 2008.
- [2] K. Nechev, "SAFT's Very High Power Li-Ion Technology," in 3rd Annual International Conference Lithium Mobile Power, San Diego, CA, 2007.
- [3] A. Y. Shenouda, "Structure and electrochemical behavior of lithium vanadate materials for lithium batteries," *Electrochimica Acta, vol. 51*, pp. 5973-5981, May 2006.
- [4] A. Y. Shenouda and K.R. Murali, "Electrochemical properties of doped

lithium titanate compounds and their performance in lithium rechargeable batteries". J. Power Sources, vol. 176, pp. 332-339, 2008.

- [5] A. Y. Shenouda and H. K. Liu, "Electrochemical behaviour of tin borophosphate negative electrodes for energy storage systems," J. Power Sources, vol. 185, pp. 1386-1391, August 2008.
- [6] A. Y. Shenouda, H. K. Liu, "Studies on electrochemical behaviour of zinc-doped LiFePO₄ for lithium battery positive electrode," J. Alloys and Compd., vol. 477, pp. 498-503, Dec. 2009.
- [7] A. Y. Shenouda, Hua K. Liu, "Preparation, Characterization, and Electrochemical Performance of Li₂CuSnO₄ and Li₂CuSnSiO₆ Electrodes for Lithium Batteries," J. Electrochem. Soc., vol. 157, pp. A 1183-A 1187, Nov. 2010.
- [8] A.Y. Shenouda E. M. El Sayed and H. K. Liu, "Preparation, Characterization and Electrochemical Performance of LiNi_xCo_yCu_zMn_{2-x-y-z}O₄ as Positive Electrodes in Lithium Rechargeable Batteries," *J. New Materials for Electrochemical Systems*", vol. 14, pp. 19-26, Feb. 2011.
- [9] S. H. Wu, K.M. Hsiao, W.R. Liu, "The preparation and characterization of olivine LiFePO₄ by a solution method," J. Power Sources, vol. 146, pp. 550-554, August 2005.
- [10] Q. R. Hu, S. L. Wang, Y. Zhang, W.H. Tang, "Synthesis of cobalt sulfide nanostructures by a facile solvothermal growth process," J. Alloys and Compd., vol. 491, pp. 707–711, Feb. 2010.
- [11] S.T. Mane, S. S. Kamble, L.P. Deshmukh, "Cobalt sulphide thin films: Chemical bath deposition, growth and properties," *Mater. Letters, vol.* 65 pp. 2639–2641, Sept. 2011.
- [12] M. Lei, X. L. Fu, Y. B. Zhang, H. J. Yang, Y. T. Huang, L. Zhang, Y. G. Wang, "Synthesis of CoS nanoplates and their ferromagnetic properties," *Mater. Letters, vol. 71, pp. 11-14, March 2012.*
- [13] M. R. Yang, W. H. Ke, S. H. Wu, "Preparation of LiFePO₄ powders by co-precipitation," J. Power Sources, vol. 146, pp. 539-543, August 2005.
- [14] A. Y. Shenouda and A. A. Momchilov, "A study on graphene/tin oxide performance as negative electrode compound for lithium battery application," J. Materials Science: Materials in Electronics, vol. 30, pp.79–90, Jan. 2019.
- [15] J. Feng, S. Xiong, Y. Qian, L. Yin, "Synthesis of nanosized cadmium oxide (CdO) as a novel high capacity anode material for Lithium-ion batteries: influence of carbon nanotubes," *Electrochimica Acta, vol. 129, pp. 107–112, Feb. 2014.*
- [16] F. Zhang, R. Zhang, J. Feng, Y. Qian, CdCO₃/Carbon nanotube nanocomposites as anode materials for advanced lithium-ion batteries," *Mater. Letters, vol. 114, pp. 115–118, Jan. 2014.*
- [17] S. Grugeon, S. Laruelle, R. Herrera-Urbina, L. Dupont, P. Poizot, J. M. Tarascon, Particle Size Effects on the Electrochemical Performance of Copper Oxides toward Lithium," J. Electrochem. Soc., vol. 148, pp. A285–A292, April 2001.
- [18] P. Poizot, S. Laruelle, S. Grugeon, L. Dupont, J. M. Tarascon, "Nanosized transition-metal oxides as negative-electrode materials for lithiumion batteries," *Nature*, vol. 407, pp. 496–499, Sept. 2000.
- [19] J. Feng, C. Wang, Y. Qian, "In situ synthesis of cadmium germanates (Cd₂Ge₂O₆)/reduced graphene oxide nanocomposites as novel high capacity anode materials for advanced lithium-*ion* batteries," *Mater. Letters, vol. 122, pp. 327-330, May 2014.*
- [20] A. L. M. Reddy, M. M. Shaijumon, S.R. Gowda, P.M. Ajayan, "coaxial Mno₂/carbon nanotube array electrodes for high-performance lithium batteries," *Nano Lett.*, vol. 9, pp. 1002–1006, March 2009.
- [21] Y. Wang, H.C. Zheng, J.Y. Lee, "Highly Reversible Lithium Storage in Porous SnO₂ Nanotubes with Coaxially Grown Carbon Nanotube Overlayers," Adv. Mater. vol. 18, pp. 645–649, March 2006.
- [22] Q. Wei, G. C. Liu, C. Zhang, X. J. Hong, Y. P. Cai, "Novel honeycomb silicon wrapped in reduced graphene oxide/CNT system as high-stability anodes for lithium-ion batteries," *Electrochimica Acta, vol. 317, pp.* 583-593, Sept. 2019.
- [23] Y. Li, Y. Fu, W. Liu, Y. Song, L. Wang, "Hollow Co-Co₃O₄@CNTs derived from ZIF-67 for *lithium* ion *batteries*," J. Alloys & Compds, vol. 784, pp. 439-446, May 2019.
- [24] Q. Tian, Y. Tian, Z. Zhang, L. Yang, S. Hirano, "Fabrication of CNT@void@SnO₂@C with tube-in-tube nanostructure as highperformance anode for *lithium*-ion *batteries*," J. Power Sources, vol. 291, pp. 173-180, Sept. 2015.
- [25] A facile one-pot synthesis of Sn/graphite/graphene nanocomposites as anode materials for lithium-ion batteries, J. Alloys & Compds, vol.809, Article 151870: pp. 1-8, Nov. 2019.

International Journal of Chemical, Materials and Biomolecular Sciences ISSN: 2415-6620 Vol:14, No:8, 2020



Atef Y. Shenouda is a Professor, Ph.D. in the Chemical and Electrometallurgy Department in CMRDI. He received his M.Sc. degree (Physical Chemistry) and his Ph.D. degree (Electrochemistry) from Cairo University in 1994 and 2000, respectively. He is currently working on developing the materials of photovoltaic solar cells and lithium batteries. He published some articles in different

international in the field of batteries and photoelectrochemical cells.



Anton A. Momchilov is a Professor, Ph.D. in the Institute of Electrochemistry and Energy Systems (IEES), Sofia, Bulgaria. He was the former Head of Lithium Systems Electrochemistry Department in IEES. He is interested in investigation and characterization of Ultra Fine Carbon suspensions, metal oxides and compounds in electrodes for rechargeable Li batteries. He participated in

University of Chemical Technology and Metallurgy, Sofia: subject - "Chemical power sources".