# Study on the Application of Lime to Improve the Rheological Properties of Polymer Modified Bitumen

A. Chegenizadeh, M. Keramatikerman, H. Nikraz

#### II. MATERIALS USED

#### A. Bitumen

Abstract-Bitumen is one of the most applicable materials in pavement engineering. It is a binding material with unique viscoelastic properties, especially when it mixes with polymer. In this study, to figure out the viscoelastic behaviour of the polymer modified with bitumen (PMB), a series of dynamic shearing rheological (DSR) tests were conducted. Four percentages of lime (i.e. 1%, 2%, 4% and 5%) were mixed with PMB and tested under four different temperatures including 64°C, 70°C, 76°C and 82°C. The results indicated that complex shearing modulus (G\*) increased by increasing the frequency due to raised resistance against deformation. The phase angle ( $\delta$ ) showed a decreasing trend by incrementing the frequency. The addition of lime percentages increased the complex modulus value and declined phase angle parameter. Increasing the temperature decreased the complex modulus and increased the phase angle until 70°C. The decreasing trend of rutting factor with increasing temperature revealed that rutting factor improved by the addition of the lime to the PMB.

*Keywords*—Rheological properties, DSR test, polymer mixed with bitumen, complex modulus, lime.

## I. INTRODUCTION

IN recent years, modified bitumen has been an interest of many research projects. Improving the viscoelastic characteristics of the bitumen has been the interest area of many studies [1]-[4]. Bulatović et al. [5] performed a series of rheological tests on natural bitumen (BIT) and PMB and indicated that PMB has a higher resistance against permanent deformation. In another study by Wu et al. [6] using DSR device, a series of laboratory aging tests and natural exposure aging tests were performed on BIT samples and different ranges of G\* and phase angle values were obtained. Eberhardsteiner et al. [7] also performed studies on ageing behaviour of the bitumen.

Hintz and Bahia [8] performed a study to figure out the fatigue behaviour of the binders of asphalt using DSR device. Moreno-Navarro et al. [9] also performed a study to assess the fatigue behaviour of the rubber in bitumen. Shen and Amirkhanian [10] investigated the effect of crumb rubber on the rheological properties of the binders. Radziszewski et al. [11] indicated that bituminous binders with the same level of hardness show variable low and high temperature properties. Veytskin et al. [12] also performed a study on mastic viscoelasticity. Toraldo et al. [13] investigated the effect of fibres on bituminous mixtures. This study aims to figure out effect of the lime on the rheological behaviour of the PMB by performing a series of DSR tests. This study is part of an ongoing investigation at Curtin University [14]. A PMB class A15E was used to conduct the tests. Table I shows the physical properties of the used bitumen.

TABLE I Physical Properties of the PMB			
Characteristics	Description		
Form/colour/odour	Black - solid at ambient temperature		
Solubility	Insoluble in water		
Specific gravity at (25%)	1.02		
Vapour pressure (25 °C)	<1 mmHg at 180 °C		
Flash point (°C)	>260 °C		
Boiling Point/Range (°C)	> 400 °C		

## B. Lime

The characteristic of the lime used in this study showed in Table II.

TABLE II				
THE PROPERTIES OF THE LIME APPLIED IN THIS STUDY				
Composition	Formula	Percentage		
Calcium Hydroxide	Ca(OH) <sub>2</sub>	80 - 95%		
Magnesium Hydroxide	Mg(OH) <sub>2</sub>	0 - 6%		
Crystalline Silica (respirable <7µm)	$SiO_2$	<1%		
Silicon Dioxide, Quartz	$SiO_2$	0-8%		

# III. METHODOLOGY

To conduct the experimental section, PMB class A15E was heated at the temperature of  $150\pm5$  °C, then lime was added and mixed manually based on determined percentages. Table III reveals the mix designs for the materials applied in this study and the temperatures that tests were ran. The DSR device was adopted to perform the tests. The selected frequency was in a range of 0.1 rad/s to 10 rad/s under 64 °C, 70 °C, 76 °C and 82 °C. A plate with 8 mm diameter used for frequency sweep test and 2 mm gap was applied between the plates. The test procedures were in accordance with AASHTO T315-10 [15] standard.

TABLE III Mix Design and Lime Percentages Used in This Study				
NO	ID	Lime (%)	Temperatures (°C)	
1	PMB	-	64, 70, 76 & 82	
2	PMB-1L	1	64, 70, 76 & 82	
3	PMB-2L	2	64, 70, 76 & 82	
4	PMB-4F	4	64, 70, 76 & 82	
5	PMB-5F	5	64, 70, 76 & 82	

Amin Chegenizadeh is with the Curtin University, Australia (e-mail: amin.chegenizadeh@curtin.edu.au).

## IV. RESULTS AND DISCUSSION

A. Relationship between Frequency and Complex Modulus  $(G^*)$ 

The relationship between complex modulus (G\*) of the PMB mixed with lime with loading frequency under 64 °C, 70 °C, 76 °C and 82 °C was shown in Figs. 1-4 respectively. An increasing inclination could be seen in all figures under the mentioned temperatures. In all graphs, the PMB has a lower value of complex modulus in comparison with the lime modified specimens. Increasing inclination of G\* parameter could be explained that at the higher frequency levels, there is a lesser time for the stresses to apply their loads to the tested specimen. Therefore, sample's ultimate shearing resistance to deformation incremented and as a result the G\* graphs raised up and vice versa.



Fig. 1 Effect of lime on complex modulus at 64 °C



Fig. 2 Effect of lime on complex modulus at 70 °C

### B. Relationship between Frequency and Phase Angle ( $\delta$ )

The relationship between phase angle of the PMB mixed with lime with loading frequency under 64°C, 70°C, 76°C and 82°C was revealed in Figs. 5-8, respectively. The results at temperatures of 64°C and 70°C showed a declining inclination by increasing the loading frequency rates. This trend causes an increasing elastic deformation of the tested specimens. The trend was contrary at 76°C and 82°C. Meaning that the graph increased by increasing the frequency values. The phase angle is a parameter that illustrates the lag between applied shearing stress and resulted strain. The higher rates of the phase angle are a sign of the greater viscosity properties of the specimens. Therefore, at higher temperatures, the specimens react more similar to viscose materials and lesser like to elastic products that results in the increase in the phase angle.



Fig. 3 Effect of lime on complex modulus at 76 °C



Fig. 4 Effect of lime on complex modulus at 82 °C

## V.CONCLUSION

In this study, viscoelastic characteristics of the PMB mixed with lime in different percentages by conducting a series of experimental tests was figured out. The lime in four percentages of 1%, 2%, 4% and 5% was mixed with the PMB and tested under temperatures of 64 °C, 70 °C, 76 °C and 82 °C. The complex modulus (G\*), phase angle ( $\delta$ ) and rutting resistance of the specimens were measured using a DSR device. The results showed that by increasing the loading frequency values, the complex modulus values were incremented, while the phase angles declined, which was due to the decreasing contact time of the plate when the stresses were applied to the samples. In addition, it was revealed that by increasing the temperature values, the complex modulus declined and the phase angles were increased until 70°C. This could be due to the changes in elastic properties of the specimens at lower temperatures to the viscosity properties at higher temperatures. The results of this study showed that 5% of lime when mixed with PMB enhances the

rutting resistance of the PMB more than other percentages of lime applied in this study.



Fig. 5 Effect of lime on phase angle at 64 °C



Fig. 6 Effect of phase angle and loading frequency at 70  $^{\circ}\mathrm{C}$ 



Fig. 7 Effect of phase angle and loading frequency at 76°C temperature



Fig. 8 Effect of phase angle and loading frequency at 82°C temperature

## REFERENCES

- Soudani, K., V. Cerezo, and S. Haddadi, 2016. Rheological characterization of bitumen modified with waste nitrile rubber (NBR). *Construction and Building Materials*. 104: p. 126-133.
- [2] Cardone, F., Frigio, F., Ferrotti, G., Canestrari, F. 2015. Influence of mineral fillers on the rheological response of polymer-modified bitumens and mastics. *Journal of Traffic and Transportation Engineering*, 2(6): p. 373-381.
- [3] Wang, C., Wang, P., Li, Y. Zhao, Y., 2015. Laboratory investigation of dynamic rheological properties of tourmaline modified bitumen. *Construction and Building Materials*. 80: p. 195-199.
- [4] Sobolev, K., Flores V., Ismael S., Rajan W., Nazimuddin M., Saltibus, N. E. 2014., The effect of fly ash on the rheological properties of bituminous materials. *Fuel*. 116: p. 471-477.
- [5] Bulatović, V. O., Rek, V., & Marković, K. J. 2012. Polymer modified bitumen. *Materials research innovations*, 16(1), 1-6.
- [6] Wu, S., Pang, L., Mo, L., Qiu, J., Zhu, G., & Xiao, Y. 2008. UV and thermal aging of pure bitumen-comparison between laboratory simulation and natural exposure aging. *Road Materials and Pavement Design*, 9(sup1), 103-113.
- [7] Eberhardsteiner, L., Füssl, J., Hofko, B., Handle, F., Hospodka, M., Blab, R., & Grothe, H. 2015. Towards a microstructural model of bitumen ageing behaviour. *International Journal of Pavement Engineering*, 16(10), 939-949.
- [8] Hintz, C., & Bahia, H. 2013. Understanding mechanisms leading to asphalt binder fatigue in the dynamic shear rheometer. *Road Materials* and Pavement Design, 14(sup2), 231-251.
- [9] Moreno-Navarro, F., Rubio-Gámez, M. C., & Jiménez Del Barco-Carrión, A. 2016. Tire crumb rubber effect on hot bituminous mixtures fatigue-cracking behaviour. *Journal of Civil Engineering and Management*, 22(1), 65-72.
- [10] Shen, J., & Amirkhanian, S. 2005. The influence of crumb rubber modifier (CRM) microstructures on the high temperature properties of CRM binders. *The International Journal of Pavement Engineering*, 6(4), 265-271.
- [11] Radziszewski, P., Kowalski, K. J., Krol, J. B., Sarnowski, M., & Piłat, J. 2014. Quality assessment of bituminous binders based on the viscoelastic properties: polish experience. *Journal of Civil Engineering* and Management, 20(1), 111-120.
- [12] Veytskin, Y., Bobko, C., & Castorena, C. 2016. Nanoindentation investigation of asphalt binder and mastic viscoelasticity. *International Journal of Pavement Engineering*, 17(4), 363-376.
- [13] Toraldo, E., Mariani, E., & Malvicini, S. 2015. Laboratory investigation into the effects of fibers on bituminous mixtures. *Journal of Civil Engineering and Management*, 21(1), 45-53.
- [14] Chegenizadeh, A., Keramatikerman, M., Nikraz, H. 2016. Flexible Pavement Modelling using Kenlayer. *Electronic Journal of Geotechnical Engineering* 21, Bund. 07, 2467-2479.
- [15] AASHTO T315-10. Standard method of test for determining the rheological properties of asphalt binder using a dynamic shear rheometer. American Association of State Highway and Transportation Officials; 2010. p. 32.